



JFE Steel Corporation

## Wire Rod (Products in Sendai)



### Functional unit

1 metric ton

### System boundary

☐ final products      ☒ intermediate products

Production stage (Raw material acquisition,  
Manufacturing) and Recycling potential

### Main specifications of the product

Production Site:

Sendai works

Representative Standards:

SC, SCR, SCM, SGD, SUM,  
SWRCH, SWRH, SWRS

Shape:

Wire Rod

Size range (mm):

φ5.5 - φ18

Registration#	JR-AW-23022E
PCR number	PA-180000-AW-05
PCR name	Steel products (except for construction use)
Publication date	15 January 2024
Verification date	21 November 2023
Verification method	Product-by-product
Verification#	JV-AW-23022
Expiration date	20 November 2028

### PCR review was conducted by:

Approval date	10 May 2023
PCR review panel chair	Yasunari Matsuno (Chiba University)

### Third party verifier\*

Takahiro Atoh

Independent verification of data & declaration in  
accordance with ISO14025

☐ internal      ☒ external

\*Auditor's name is stated if system certification has been performed.

### Company Information

JFE Steel Corporation      Planning &amp; Marketing Dept., Steel Bar &amp; Wire Rod Division

<https://www.jfe-steel.co.jp/en/index.html>

## 1. Results of life cycle impact assessment (LCIA)

Stage Parameter	Production stage (cradle to gate) [A1],[A2] and [A3]	Unit
Global warming IPCC2013 GWP100a	1.0E+03	kg-CO <sub>2</sub> eq
Acidification	5.8E-01	kg-SO <sub>2</sub> eq
Photochemical ozone	3.3E-03	kg-PO <sub>4</sub> <sup>3-</sup> eq

Stage Parameter	Unit	Total	[A1][A2] Raw material acquisition	[A3] Manufacturing	[D] Recycling potential
Global warming IPCC2013 GWP100a	kg-CO <sub>2</sub> eq	1.0E+03	2.4E+02	7.6E+02	3.4E+02
Ozone layer destruction	kg-CFC-11eq	2.2E-07	1.7E-07	5.7E-08	6.1E-08
Acidification	kg-SO <sub>2</sub> eq	5.8E-01	2.6E-01	3.2E-01	5.2E-01
Photochemical ozone	kg-C <sub>2</sub> H <sub>4</sub> eq	1.6E-02	1.7E-03	1.5E-02	7.3E-02
Eutrophication	kg-PO <sub>4</sub> <sup>3-</sup> eq	3.3E-03	4.9E-06	3.3E-03	6.2E-03

## 2. Life cycle inventory analysis (LCI)

Parameter		Unit
Non-renewable material resources	2.3E+01	kg
Non-renewable energy resources	1.6E+04	MJ
Renewable material resources	1.3E+01	kg
Renewable primary energy	2.9E+02	MJ
Consumption of freshwater	1.7E+00	m <sup>3</sup>

## 3. Material composition

Material		Unit
iron [Fe]	≥84.2	wt%
carbon [C]	≤1.10	wt%
silicon [Si]	≤3.00	wt%
manganese [Mn]	≤3.00	wt%
phosphorus [P]	≤0.15	wt%
sulfur [S]	≤0.45	wt%
copper [Cu]	≤0.60	wt%
nickel [Ni]	≤4.00	wt%
chromium [Cr]	≤2.50	wt%
molybdenum [Mo]	≤1.00	wt%

## 4. Waste to disposal

Parameter		Unit
Hazardous waste	0.0E+00	kg
Non-hazardous waste.	8.4E-01	kg

\*Data derived from LCA and not assigned to the impact categories of LCIA

## 5. Additional explanation

- Scrap recycling potential is calculated based on ISO 20915/JIS Q 20915 and shown as [D] in table 1. Recycling ratio used in this calculation is 93.0%. (Using data is 2018FY from The Japan Iron and Steel Federation, The Japan ferrous raw materials association and The Japan Steel Can recycling Association).
- The basic unit data of power consumption is the average of 10 electric power suppliers of Japan in 2014FY.
- Each item (except iron) in table 3 is the maximum value of all product standards covered by this EPD.
- Primary data in 2021 is used.



SuMPO EPD

Type III Environmental Declaration (EPD)

Registration number : JR-AW-23022E

Japan EPD Program by SuMPO

Sustainable Management Promotion Organization  
14-8, Uchikanda 1-chome, Chiyoda-ku, Tokyo Japan  
<https://ecoleaf-label.jp/>

#### 6-1. Supplementary environmental information

The production site is certified to ISO 14001.

#### 6-2. Regulated hazardous substances

Substance	CAS No.	Reference to standards or regulations
manganese [Mn]	7349-96-5	• Industrial Safety and Health Act
nickel [Ni]	7440-02-0	• Industrial Safety and Health Act
chromium [Cr]	7440-47-3	• Industrial Safety and Health Act
molybdenum [Mo]	7439-98-7	• Industrial Safety and Health Act
copper [Cu]	7440-50-8	• Industrial Safety and Health Act
lead [Pb]	7439-92-1	• Industrial Safety and Health Act

#### 7. Assumptions of secondary data used

IDEA v2.1.3 database is used. Steel scrap data (JP-AJ-0001) from the Japan Iron and Steel Federation are used.

#### 8. Remarks

- March, 2025; Change from the EcoLeaf mark to the SuMPO EPD mark.

- For data quantification, please refer to PCR and Rules on quantification and declaration.
- Comparative assertion is permitted only when Rules on quantification and declaration are satisfied.  
(Reference URL : <https://ecoleaf-label.jp/regulation/>)

Registration number : JR-AW-23022E