Japan EPD Program by SuMPO Sustainable Management Promotion Organization 14-8, Uchikanda 1-chome, Chiyoda-ku, Tokyo Japan https://ecoleaf-label.jp/



KUROSAWA Highly Durable PCaPC Posttension Girder & Beam Products (Fc=60N/mm2)





## **Functional unit**

1m³

## System boundary

□ final products ■ intermediate products Product Stage (Cradle to Gate: A1-A3) \*A4, A5, B1-B7, C1-C4 are excluded from the system boundary

## Main specifications of the product

Product Number: Post-PC-GB-60 Specified Design Strenth: 60N/mm2 Product Mass: 2,550kg per 1m<sup>2</sup> Kanto Sakuragawa Factory

#### JR-BH-23002E **Registration# PCR number** PA172290-BH-04 PCR name Precast Concrete PC (intermediate goods) **Publication date** 4/19/2023 Verification date 4/12/2023 Verification method Product-by-product Verification# JV-BH-23002 **Expiration date** 4/11/2028 PCR review was conducted by: **Approval date** 1/6/2023 Ken Yamagishi PCR review (Affiliation:Sustainable Management Promotion panel chair Organization) Third party verifier\*

Shinichi Inoue

Independent verification of data & declaration in accordance with ISO14025 and ISO 21930

□internal

external

\*Auditor's name is stated if system certification has been performed.

Registration number : JR-BH-23002E

# **Company Information**

KUROSAWA CONSTRUCTION CO., LTD Marketing Depertment TEL +813-6302-0222 URL:https://www.kurosawakensetu.co.jp/



Acidification

Eutrophication

Photochemical ozone

Resources consumption

## EcoLeaf

Type III Environmental Declaration (EPD)Registration number : JR-BH-23002E

### Japan EPD Program by SuMPO

Sustainable Management Promotion Organization 14-8, Uchikanda 1-chome, Chiyoda-ku, Tokyo Japan https://ecoleaf-label.jp/

1. Results of life cycle impact assessment (LCIA)									
			75%	80%	85% 90	0% 95%	6 100%		
Global warming IPCC2013 GWP100a	1000	kg-CO2eq			95.6%		<mark>1.7%</mark> 2.7%		
Acidification	0.52	kg-SO2eq		84.8%	7.5%		7.6%		
Resources consumption	0.068	kg-Sbeq			99.7%		0.1% 0.2%		
A1: Raw material acquisition A2: Production A3: Distribution									
Stage Parameter	Unit	Total	A1: Raw material acquisition	A2: Production	A3: Distribution				
Global warming IPCC2013 GWP100a	kg-CO <sub>2</sub> eq	1.0E+03	9.8E+02	1.7E+01	2.8E+01				
Ozone layer destruction	kg-CFC-11eq	1.2E-06	7.7E-07	1.3E-10	4.3E-07				

4.4E-01

3.3E-03

3.2E-05

6.8E-02

3.9E-02

7.9E-05

1.2E-13

7.1E-05

2. Life cycle inventory analysis (LCI)					
Parameter		Unit			
Non-renewable material resources	2.8E+03	kg			
Non-renewable energy resources	3.2E+02	kg			
Non-renewable energy resources	1.1E+04	MJ			
Renewable material resources	1.4E+02	kg			
Renewable primary energy	7.8E+01	MJ			
Consumption of freshwater	1.5E+00	m³			

kg-SO<sub>2</sub>eq

 $kg-C_2H_4eq$ 

kg-PO<sub>4</sub><sup>3-</sup>eq

kg-Sbeq

5.2E-01

3.7E-02

2.3E-04

6.8E-02

3. Material composition					
Material		Unit			
Cement	18	%			
Admixture	0.24	%			
Aggregates	75	%			
Rebars and PC wires	5.2	%			
Other materials	1.2	%			
-	-	-			

4.0E-02

3.3E-02

1.9E-04

1.2E-04

4. Waste to disposal						
Parameter		Unit				
Hazardous waste	0.00E+00	kg				
Non-hazardous waste.	3.5E+01	kg				

\*Data derived from LCA and not assigned to the impact categories of LCIA

5. Additional explanation

<Scope of Lifecycle Stages>

This declaration result consists of the Cradle to Gate stages (A1:Raw material acquisition, A2:Transport,

A3:Manufacturing).

<Outline of Transport Scenarios>

• For transportation of raw material procurement, the scenarios in PCR Annex B were applied for the means of transportation, loading rate, and domestic transportation at the import destination when there was difficulty in identifying the primary data. When transportation involved marine transportation and domestic transportation, the distance was calculated based on the primary data.

Sustainable Management Promotion Organization 14-8, Uchikanda 1-chome, Chiyoda-ku, Tokyo Japan https://ecoleaf-label.jp/

6-1. Supplementary environmental information

• No toxic substances in the product.

• The design service life of this product shall be 200 years. The specified design service life of the building's structural frame has been verified by a third-party organization, the Center for Better Living (report on verification results dated May 25, 2020).

• The installing of prestress into the structural frame and members of high-strength concrete in advance prevents cracks that cause deterioration and suppresses the intrusion of deterioration factors such as carbonization, resulting in a highly durable product with significantly less deterioration over time.

 $\boldsymbol{\cdot}$  This product's declaration URL:

https://ecoleaf-label.jp/en/epd/813

7. Assumptions of secondary data used Based on the IDEA v2.1.3 and the intensity data v1.12 registered in Japan EPD Program by SuMPO

Remarks

- For data quantification, please refer to PCR and Rules on quantification and declaration.
- Comparative assertion is permitted only when Rules on quantification and declaration are satisfied. (Reference URL : https://ecoleaf-label.jp/regulation/)

Registration number : JR-BH-23002E